

## Marco Compound # S1015

### 70 Durometer, Orange, High Temperature Silicone

#### Technical Datasheet

**Common Names:**

Silicone, VQM

**General Description:**

Silicones are excellent seal materials for extreme temperature in static applications. Silicones can be synthesized with a wide variety of properties and compositions. Please contact [sales@newtopsrinjection.com](mailto:sales@newtopsrinjection.com) for assistance in selecting a specialized compound when increased resistance to temperature, lubricants, or physical properties is required.

**Features:**

- High Temperature
- Excellent heat and compression resistance
- Excellent resistance to oxygen, ozone and sunlight
- Good chemical resistance
- Resistance to fungal and biological attack
- Flexible
- Good electrical insulation

**Limitations:**

- Not recommended for dynamic application
- Concentrated solvents, oils, concentrated acids, diluted sodium hydroxide.
- Poor abrasion resistance
- Low strength
- High gas permeability

**Service Temperature:**

-65 to 500°F (-54 to 260°C)

Higher Spikes up to 550°F (287°C) - Short Duration

**Specification:**

ASTM 2000 M5GE706 A19 B37 EO16 EO36 Z1 (Z1 = High Temp.)

**PHYSICAL PROPERTY STANDARDS**

ORIGINAL PROPERTIES	ASTM D2000 Requirements	Typical Test Results
Hardness, Shore A	70 +/- 5	69
Color	Orange	Orange
Tensile Strength, psi	865	940
Ultimate Elongation, %	150	220
Specific Gravity		1.18

This information is to the best of our knowledge accurate and reliable. However, Newtop Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.

Request a Quote

HEAT RESISTANCE – A19, ASTM D 573 (70 hrs. @ 225°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A	+10	+5
Tensile Strength Change, %, max.	-25	+1
Ultimate Elongation Change, %, max.	-30	-6

COMPRESSION SET – B37, ASTM D 325 Method B (22 hrs. @ 175°C)	ASTM D2000 Requirements	Typical Test Results
Permanent Set, %, max.	25	20

FLUID RESISTANCE –ASTM #1 Oil – EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A	0 to -15	-5
Tensile Strength Change, %, max.	-20	-14
Ultimate Elongation Change, %, max.	-20	+1
Volume Change, %	0 to +10	+2

FLUID RESISTANCE – IRM 903 Oil, -EO36, ASTM D 471 (70 hrs. @ 150°C)	ASTM D2000 Requirements	Typical Test Results
Hardness Change, points, Shore A, max.	-30	-19
Volume Change, %, max.	+ 60	+13

This information is to the best of our knowledge accurate and reliable. However, Newtop Rubber makes no warranty, expressed or implied, that parts manufactured from this material will perform satisfactorily in the customer's application. It's the customer's responsibility to evaluate parts prior to use.